



Service Center (SGS and IMME Mongolia)



SGS IMME MONGOLIA LLC

INSPECTION REPORT

Company : Darkhan Metallurgical Plant

Location: Tumortei Terminal

Date: 2024.4.6

Sample No:	Product weight	H ₂ O	Fe	S	Al ₂ O ₃	SiO ₂	TiO ₂	P	Number of Car:	
	ton	%	%	%	%	%	%	%	pcs	
TLot 29	1	671.35	2.18	58.36	0.31	2.14	6.45	0.38	0.01	10
	2	657.65	2.07	59.37	0.30	1.96	5.31	0.32	<0.01	10
	3	704.30	2.06	57.86	0.30	2.15	6.37	0.33	<0.01	10
	4	710.85	2.04	60.28	0.39	1.53	4.99	0.27	0.02	10
	5	419.20	2.12	57.56	0.41	1.85	6.61	0.36	<0.01	6
Average result*	3,163.35	2.09	58.78	0.34	1.93	5.89	0.33	0.01	46	

NOTE: *Average result of all analytes is for summary of product weight.
This result format of the inspection sample only for DMP's internal use only.

Signature



SGS-IMME Mongolia LLC